Scotch[™] **Super 33+ Vinyl Electrical Tape**

Data Sheet

Product Description:

Scotch™ Super 33+ Vinyl Electrical Tape is a premium grade, 7 mil thick, all-weather vinyl-insulating tape. It is designed to perform continuously in ambient temperatures up to 105°C (220°F). The tape is conformable for cold weather application down to −18°C (0°F). It has excellent resistance to abrasion, moisture, alkalies, acids, corrosion and varying weather conditions (including ultraviolet exposure). The combination of elastic backing and aggressive adhesive provides moisture-tight electrical and mechanical protection with minimum bulk. Super 33+ is an Underwriters' Laboratories Listed and Canadian Standards Association Certified "Insulating Tape".

- UL Listed; UL 510 Standard "Insulating Tape" (product category OANZ), File E129200
- CSA Certification; Standard C22.2 No.197-M1983 "PVC Insulating Tape," File LR 48769
- Polyvinyl chloride (PVC) backing.
- Pressure-sensitive rubber based adhesive.
- Compatible with solid dielectric cable insulations.
- Compatible with rubber and synthetic splicing compounds, as well as epoxy and polyurethane resins.
- Inhibits corrosion of electrical conductors.
- For indoor or outdoor applications.

Applications:

- Primary electrical insulation for all wire and cable splices rated up to 600 volts and 105°C (220°F).
- Primary electrical insulation for 600 volt bus applications, and protective jacketing for low and high voltage bus.
- Protective jacketing for high voltage cable splices and repairs.
- Harnessing of wires and cables.

Typical Data / **Physical Properties:**

Temperature Rating: 80°C (176°F)

UL 510

CSA

C22.2 No. 197-M1983

 $-18^{\circ}C (0^{\circ}F)$ Handling

Continuous

Operation 105°C (220°F)

Color Black

Thickness

ASTM D1000 7 mils

Adhesion to Steel

ASTM D1000

22°C (72°F) 28 oz./in. $-18^{\circ}C (0^{\circ}F)$ 60 oz./in.

Adhesion to Backing

ASTM D1000

22°C (72°F) 25 oz./in. -18°C (0°F) 60 oz./in.

Breaking Strength

ASTM D₁000

22°C (72°F) 15lbs./in.

Ultimate Elongation

ASTM D1000

22°C (72°F) 250% $-18^{\circ}C (0^{\circ}F)$ 100%

Flammability (Maximum)

UL 510 1 sec **ASTM D1000** 4 sec.

Accelerated Aging

ASTM D1000 80%

Flagging

ASTM D1000 <0.1 inch

Telescoping

24 Hours @ 50°C < 0.1 inch (120°F).

Electrical Properties:

Voltage Rating

UL 510 600V

Dielectric Strength

ASTM D1000

Standard Condition 1150

V/mil

High Humidity 90% of std.

Insulation Resistance

ASTM D1000 $>1 \times 10^6$

megohms

(High Humidity Method)

Note: These are typical values and should not be used for specification purposes.

Specification:

Product:

The tape is based on polyvinyl chloride (PVC) and/or its copolymers and has a rubberbased, pressure-sensitive adhesive. The tape shall be 7 mils thick, and be UL Listed and marked per UL Standard 510 as "Flame Retardant, Cold and Weather Resistant." The tape must be applicable at temperatures ranging from 0°F through 100°F (-18°C through 38°C) without loss of physical properties. The tape shall be classified for use in both indoor and outdoor environments. The tape shall be compatible with synthetic cable insulations, jackets and splicing compounds. The tape will remain stable and will not telescope more than 0.1 inches when maintained at temperatures below 120°F (50°C).

Engineering/Architec tural Specification:

Primary electrical insulation (branch wiring in wet or dry locations): All splices for 600 volt wire rated 105°C (220°F) and below shall be insulated with a minimum of two half–lapped layers of Scotch Super 33+ Vinyl Electrical Tape. All connectors having irregular surfaces shall be padded with Scotchfil™ Electrical Insulation Putty or Scotch 130C Rubber Splicing Tape prior to insulating with Scotch Super 33+ Vinyl Electrical Tape.

Mechanical protection (outer jacketing): All rubber and thermoplastic insulating high voltage power cable tape splices and repairs shall be overwrapped with at least two half-lapped layers of Scotch Super 33+ Vinyl Electrical Tape

Installation Techniques:

The tape shall be applied in halflapped layers with sufficient tension to produce a uniform wind (for most applications this tension will reduce the tape's width to approximately 5/8 of its original width). On pigtail splices, the tape shall be wrapped beyond the end of the wires and then folded back, leaving a protective cushion to resist cutthrough. Wrap tape up-hill, taping from a smaller diameter surface to a larger diameter surface. Apply the tape with no tension on the last wrap to prevent flagging.

Shelf Life:

Scotch Super 33+ Vinyl Electrical Tape complies with the requirements of UL 510 for storage. When maintained under normal storage conditions the tape will remain stable and has a five year shelf-life.

Availability:

Scotch Super 33+ Vinyl Electrical Tape is available from your local 3M authorized distributor in the following standard roll sizes:

3/4 in. x 66 ft.

3/4 in. x 44 ft.

3/4 in. x 20 ft.

Other lengths and widths are available by special request.

Scotch and Scotchfil are trademarks of 3M.

Important Notice

All statements, technical information and recommendations related to the Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized officer of the Seller. The statements contained herein are made in lieu

of all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY, INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY, FOR ANY INJURY OR FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS THAT WERE DEFECTIVE.



Electrical Products Division

6801 River Place Blvd. Austin, TX 78726-9000 800 245 3573 http://www.3m.com/elpd