## **POLYKEN**<sup>®</sup>

## 108FR

## **FR Double-Coated Cloth Tape**

Release Liner	Carrier:	Cloth		
Adhesive	Adhesive:	Rubber		
Carrier	Liner:	Blue LDPE		
Adhesive	Colors:	Natural or Black (adhesive color)		
	Specifications	FAR 25.853(a), BMS 5-133, BAC5034-4 Sec		
		5.1.a(1)(b), Douglas DMS 1971, Lockheed LAC		
		C-24-1257, Embraer MEP 06-048. Listed FK05-		
		121 & FK05-197; ABD0031 Paragraph 7.4		
	Standard Size	<b>48</b> mm x 23M, 72mm x 23M		
	Applic	ations		
Carpet installation on interior floors and	<ul> <li>Mounting &amp; holding for general shop &amp; machine</li> </ul>			
stairs of aircraft		handling.		
Acrylic plastic sheeting applications.				
, lei yne plustie sneeting uppheutions.		Benefits		
Features		Benefits		
<i>,</i>	•	Good strength and elongation for easy		
Features	•			
Features	•	Good strength and elongation for easy		
Features	•	Good strength and elongation for easy tear, application and removal		
<b>Features</b> Cloth reinforcement	•	Good strength and elongation for easy tear, application and removal Conformable and moisture resistant		
<b>Features</b> Cloth reinforcement	•	Good strength and elongation for easy tear, application and removal Conformable and moisture resistant Clean removal from most surfaces Aggressive bond for secure hold Repositionable adhesive for easy installation		
<b>Features</b> Cloth reinforcement	•	Good strength and elongation for easy tear, application and removal Conformable and moisture resistant Clean removal from most surfaces Aggressive bond for secure hold		

Physical Properties						
	Standard UOM	Metric UOM	Test Method	_		
Total Thickness	15 mils	381 mic	ASTM D-1000			
Adhesion to Steel (air)	60 oz/in	6.57 N/cm	PSTC-101			
Tensile Strength	55 lb/in	96.32 N/cm	ASTM D-1000			
Weight	13 oz/sq yd	472.9 g/m <sup>2</sup>	ASTM D-1000			
Operating Temperature	40 to 200 °F	4 to 93 °C				
Exiting Time	1.5 sec		FAR 25.853(a)			
Burn Length	4.5"		FAR 25.853(a)			
Drip Exiting	N/A		FAR 25.853(a)			

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F Standard Shelf Life (at 25C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryplastics.com Nijverheidsstraat 10 2260 Oevel (Westerlo) Belgium 32-014-722500 Fax 32-014-722570 12/13/13