

## PRODUCT DATA SHEET

# #7700 Jaylastic® Hybrid – MIDDLEWEIGHT ADHESIVE STRETCH TAPE

## **DESCRIPTION:**

- ♣ Bleached White Cotton/Spandex® blended fabric tape (non-crepe)
- Multi-purpose Strapping Tape
- White synthetic rubber adhesive formulation w/ Zinc Oxide
- 100% Latex Free
- Non-sterile, for external usage and disposable.
- Hand Tearable
- Sport stretch product with superior memory quality
- Stable Adhesive Coating when exposed to heat
- ♣ Store Cool & Dry for maximum performance
- ♣ Made in USA by Jaybird & Mais, Inc.



## **PHYSICAL PROPERTIES\*:**

Tensile Strength (PSTC-31) 34 lbs/linear inch Adhesion 180° Peel to SS (PSTC-101) 18 ounces/linear inch

Water Immersion (15 minutes)

Good adhesion to Steel, no residue

Rolling Ball (PSTC-6) 1 linear inch Thickness 20 mils [.508mm]

## STANDARD SIZE/PACKAGING:

Product No.	Size	Rolls/Cs
7700-1050	1" x 5 yards (2,5cm x 4,6m)	48
7700-2050	2" x 5 yards (5,0cm x 4,6m)	24
7700-3050	3" x 5 yards (7,5cm x 4,6m)	16

## Width Specification

Tolerance	+/80mm (.03125 inches)
Length Specification	
Tolerance 5 yards (4,6 meters)	+/- 22.5cm (9 inches)

## STORAGE:

The above product should be stored in a cool dry environment for best results of product performance. Average recommended temperature for storage:  $60^{\circ}$  to  $72^{\circ}$  Fahrenheit (19.4° to 22.8° Centigrade)

Jaybird & Mais, Inc. reserves the right to change specifications of this product at anytime without prior notice.

Please contact Jaybird & Mais, Inc. for additional product information.

<sup>\*</sup> Pressure Sensitive Tape Council methods used when applicable. Testing represents typical performance values (averages). Technical information provided by Jaybird & Mais, Inc. is based on experience and/or tests believed to be reliable, but their accuracy is not guaranteed and the results may not be relevant to every user's application. For this reason Jaybird & Mais, Inc. does not accept responsibility or liability, direct or consequential, arising from reliance upon any information provided and the user should determine the suitability of the products for their intended use. Mar-6, 2015