

# tesa® 4987

## **Product Information**



## Double-sided 5mil non-woven tape

## **Product Description**

tesa® 4987 is a translucent double-sided self-adhesive tape consisting of a non-woven backing and a tackified acrylic adhesive.

tesa® 4987 features especially:

- · Good shear resistance
- · A good conjunction of high initial tack and ultimate adhesion level even to rough surfaces
- · Good resistance to environmental conditions such as light, elevated temperatures etc.

## **Application Fields**

- · Fixing of furniture trims, profiles and window blinds
- · Mounting of heating elements
- · Splicing of corrugated cardboard
- Lamination of foam and rubber substrates

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul> <li>Type of liner</li> </ul>	glassine	<ul> <li>Total thickness</li> </ul>	125 μm
<ul> <li>Weight of liner</li> </ul>	100 g/m <sup>2</sup>		4.9 mils
<ul> <li>Backing material</li> </ul>	non-woven	<ul> <li>Color</li> </ul>	translucent
<ul> <li>Type of adhesive</li> </ul>	tackified acrylic	<ul> <li>Color of liner</li> </ul>	white
		<ul> <li>Thickness of liner</li> </ul>	84 μm
			3.3 mils

### **Properties/Performance Values**

<ul><li> Elongation at break</li><li> Tensile strength</li></ul>	3 % 8 N/cm 4.6 lbs/in	<ul> <li>Static shear resistance at 23°C</li> <li>Static shear resistance at 40°C</li> <li>Tack</li> </ul>	good medium good
<ul> <li>Ageing resistance (UV)</li> <li>Chemical resistance</li> </ul>	good good	Temperature resistance long term	80 °C 176 °F
<ul><li>Humidity resistance</li><li>Softener resistance</li></ul>	good medium	<ul> <li>Temperature resistance min.</li> <li>Temperature resistance short term</li> </ul>	-40 °C -40 °F 200 °C 392 °F



# tesa® 4987

## **Product Information**

### Adhesion to Values

ABS (initial)	8 N/cm	<ul> <li>PET (after 14 days)</li> </ul>	8.7 N/cm
	73.1 oz/in		79.5 oz/in
<ul> <li>ABS (after 14 days)</li> </ul>	10.8 N/cm	<ul> <li>PP (initial)</li> </ul>	5.6 N/cm
	98.7 oz/in		51.2 oz/in
<ul> <li>Aluminium (initial)</li> </ul>	7.7 N/cm	<ul> <li>PP (after 14 days)</li> </ul>	6.2 N/cm
	70.3 oz/in		56.6 oz/in
<ul> <li>Aluminium (after 14 days)</li> </ul>	10.1 N/cm	<ul> <li>PS (initial)</li> </ul>	8.5 N/cm
	92.3 oz/in		77.7 oz/in
<ul> <li>PC (initial)</li> </ul>	9.3 N/cm	<ul> <li>PS (after 14 days)</li> </ul>	10.3 N/cm
	85 oz/in		94.1 oz/in
<ul> <li>PC (after 14 days)</li> </ul>	10.4 N/cm	<ul> <li>PVC (initial)</li> </ul>	7 N/cm
	95 oz/in		64 oz/in
PE (initial)	4.1 N/cm	<ul> <li>PVC (after 14 days)</li> </ul>	11.4 N/cm
	37.5 oz/in		104.2 oz/in
PE (after 14 days)	4.8 N/cm	<ul> <li>Steel (initial)</li> </ul>	9 N/cm
	43.9 oz/in		82.2 oz/in
<ul> <li>PET (initial)</li> </ul>	6.9 N/cm	<ul> <li>Steel (after 14 days)</li> </ul>	11.2 N/cm
	63 oz/in		102.3 oz/in

## Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.