



Adhesion Promoter 111

Technical Data

January, 2006

Product Description 3M™ Adhesion Promoter 111 is an isopropyl alcohol based solution used to promote better and faster adhesion of 3M™ VHB™ Tapes to various surfaces including bare metals, galvanized steel, and painted surfaces. Since surfaces and paint formulations vary considerably, each application should be verified through testing.

- Features**
- Higher bond strength.
 - Increased tape adhesion build rate at both normal and cooler temperatures.
 - Isopropyl alcohol based solvent system.
 - Non-offensive odor.
 - Very quick drying.
 - Can clean and promote adhesion in one step provided the surface is relatively clean and free of wax, grease, oil, and loose particles.

Typical Physical Properties **Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

Solvent:	Isopropyl alcohol (IPA)
Active Ingredients:	Less than 5% by weight
VOC's	780 g/l
Color:	Clear
Flashpoint:	11°C (52°F)
Coverage:	Approximately 19 m ² /l (800 ft ² /gal) based on 0.002" wet coating thickness. Can vary greatly depending on method of application.
Drying Time:	Approximately 1 minute depending on coating thickness, temperature, and humidity.
Availability:	250 ml bottle, 1 gallon can

Application Instructions

Surface must be clean, dry, and free of wax, oil, grease and loose particles.
Substrate must be unified.
Contaminated surfaces must be cleaned with an appropriate cleaner and/or a 50/50 mixture of isopropyl alcohol and water.*
Apply a thin, uniform coating to the bonding surface before application of 3M™ VHB™ Tape. Use the minimum amount that will fully coat the area to be taped.
Application may be done with a clean lint-free cloth, pad, felt tipped dauber, absorbent paper towel or disposable tissue. Brushes, rollers, or spraying tend to apply excessive amounts of 3M™ Adhesion Promoter 111 and should therefore be avoided.
Allow to dry completely prior to application of tape. Depending on temperature and humidity, the drying and reacting time of 3M adhesion promoter 111 can vary. Typical drying time will be 1-2 minutes. Forced, hot air drying of 3M adhesion promoter 111 is acceptable, but remember that 3M adhesion promoter 111 is flammable and must not be used near any open flames or ignition sources.
Apply tape within 8 hours, or reapply 3M adhesion promoter 111.
REPLACE CAP WHEN NOT IN USE. 3M adhesion promoter 111 is reactive with water including moisture (humidity) in air.
*When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

3M™ Adhesion Promoter 111

Clean Up

3M™ Adhesion Promoter 111 can be removed from unwanted surfaces with straight isopropyl alcohol (IPA) or a blend of IPA and water. Rubbing Alcohol is typically 70% IPA and 30% water.*

Excessive 3M adhesion promoter 111 may cause a dull white appearance on the surface. A small amount of chalking should not adversely affect the adhesive strength. If desired, for appearance purposes, the dull white chalking may be removed after tape application with either a clean dry cloth or a clean cloth that is slightly wet with isopropyl alcohol. Before tape application, the dull white chalking may be removed with a clean cloth that is only slightly wet with more 3M adhesion promoter 111.

*When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Storage

3M adhesion promoter 111 will tolerate storage and shipment temperatures from -40°C (-40°F) to 66°C (150°F), but needs to be at a minimum of 10°C (50°F) when applied. Do not store in plastic container for more than 8 hours. Many plastics do not provide an adequate vapor barrier to prevent loss of liquid.

Shelf Life

One year from date of shipment. Once opened, it is best to use within one month. Shelf life may be decreased, especially if open or poorly resealed container is continuously exposed to hot or humid environments. Properly dispose of any 3M adhesion promoter 111 that is either cloudy or has white precipitate on the bottom of the container.

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



Industrial Business Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (fax)
www.3M.com/industrial



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2006 70-0709-3983-3 (2/06)