




296FR

Flame Retardant Fiberglass Tape



- Backing:** Fiberglass Cloth
- Adhesive:** Bromide-Free Acrylic
- Liner:** LDPE Film
- Colors:** White Printed

Specifications: Meets FAR 25.853(a) & 25.855(d), BMS5-146 Airbus ABD0031, Para 7.3.2& 7.4; Boeing 737-SL-25-115-B, 757-SL-25-085-B, 747-SL-25-195-B, 767-SL-25-112-B, 777-SL-25-037-B

Standard Sizes*: 1in, 2in, 3in and 4in x 36yd

Applications

- Cargo pit applications for freight carrying aircraft
- Challenging applications where high adhesion and flame resistance is critical
- Seaming and repairing cargo compartment liners
- Covering pins & rivets
- Metal surface protection during soldering or welding

Features

- Fiberglass Cloth
- Bromide-Free Acrylic Adhesive
- Complies with FAR 25.853(a) & 25.855(d)

Benefits

- Super high tensile strength
- Resists flame penetration for added safety
- Lightweight construction - saves money
- Conformable to handle curves and corners
- Meets EU Directive 76/769/EEC
- Repositionable and clean removal
- Resists flagging and lifting
- Meets requirements for use in aircraft cargo compartments

Physical Properties

	Standard UOM	Metric UOM	Test Method
Total Thickness	7.0 mils	177.8 mic	ASTM D-1000
Adhesion to Steel	45 oz/in	4.93 N/cm	PSTC-101
Tensile Strength	134 lb/in	234.67 N/cm	ASTM D-1000
Weight	6.8 oz/yd ²	210 g/m ²	ASTM D-1000
Operating Temperature	-40 to 275°F	-40 to 135° C	
Exiting Time	0.66 sec		FAR 25.853(a)/25.855(d)
Burn Length	3"		FAR 25.853(a)
Flame Penetration	N/A		FAR 25.855(d)
Drip Exiting	N/A		FAR 25.853(a)
After Glow	0 sec		FAR 25.855(d)

* Other sizes may be available. Contact your sales representative.
 Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F
 Standard Shelf Life (at 25C): 24 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038
 1-800-343-7875 Fax 1-800-328-4822
 www.berryplastics.com

Nijverheidsstraat 10
 2260 Oevel (Westerlo) Belgium
 32-014-722500 Fax 32-014-722570
 8/30/13